



## MELAMINE FORMALDEHYDE RESINS

Product Nomenclature	Type	Colour *	Viscosity at 25°C*	% Non volatiles #	Acid value mgs KOH/gm	% Free Formaldehyde	M.T. Tolerance \$	Xylene Tolerance @	Remarks / Recommended Usages
R 5802	Butylated MF	1 Max	5-10.7	60±2	1.5 Max	3 Max	1 : 4 - 6	1 : Infinite	High reactive. Used for curing of short oil alkyds, imparting excellent hardness, sharp gloss and mar-proofness to stoving system
R 5803	Butylated MF	1 Max	5-10.7	65±2	1.5 Max	3 Max	1 : Infinite	1 : Infinite	Low reactive. Used in economical stoving finishes, roller coating enamel etc.
R 5804	Butylated MF	1 Max	10.7-17.6	65±2	1.5 Max	3 Max	1 : 6 - 8	1 : Infinite	Medium reactive. It is fast curing & imparts excellent gloss & hardness when cured with short oil alkyd.
R 5806	Butylated MF (High Solid)	1 Max	22.7-63.4	80±2	1.5 Max	3 Max	1 : 4 - 10	1 : Infinite	Fast curing, It is used in curing of short oil alkyds, acrylic imparting excellent hardness sharp gloss and mar-proofness
R-5809	Butylated MF	1 Max	3-10 ps	65±2	1 Max	1 Max	1 : 7	1 : Infinite	Fast Curing, used as Cross linker for Alkyds, Polyesters & Acrylic resins
R-5810	Methylated Melamine Formaldehyde Resin	0-1	6.27-12.9 ps	65±2	1 Max	3 Max	Non- Compatible	01 : 12	Finishes for refrigerators, quality furniture finishes and Automotive coatings

## UREA FORMALDEHYDE RESINS

Product Nomenclature	Type	Colour *	Viscosity at 25°C*	% Non volatiles #	Acid value mgs KOH/gm	% Free Formaldehyde	M.T. Tolerance \$	Xylene Tolerance @	Remarks / Recommended Usages
R 5813	Butylated UF	1 Max	17.6-27	65±2	1.5 Max	3 Max	1 : 1.5-3.5	1 : Infinite	It is used for epoxy finishes for refrigerators, furniture and flow agent
R 5818	ISO Butylated UF	1 Max	8.84-12.9	60±2	1.5 Max	3 Max	1 : 1-2.5	1 : 20 Min	Fast curing. It is used for wood and screen finishes, finishes for quality furniture and flow agent for epoxy finishes
R 5819	Butylated Urea Formaldehyde Resin	1 Max	10.7-22.7	60±2	3.5 Max	0.5 Max	1 : 2-3	Infinite	Acid cured wood finishes, Stoving enamels, Varnishes

## RESINS & PLASTICS LTD.

Regd. Off.: Plot No. A-8, Marol Industrial Estate of MIDC, Cross Road B, Street No.5, Andheri (E), Mumbai - 400 093. India. Tel.: +91- 22- 6198 7000 Email : info@resplast.com

Although the information contained in this Product Data Sheet is believed to be correct as of the date hereof; Resins & Plastics Ltd. makes no representation the completeness of accuracy in this Data Sheet. Those who use this product described herein must determine the appropriate manner for processing the product to ensure the safety and quality. In no event shall Resins & Plastics Ltd. be responsible for damages of any nature resulting from the use of or reliance upon the information contained herein.