



ACRYLIC RESINS (THERMOPLASTIC)

Product Nomenclature	Non-Volatiles 50°C/30min.	Solvent	Viscosity in Stokes at 25°C(G)	Acid Value (max.) (mgs. of KOH/gm)	Characteristics	Recommended Usages
Replakryl 912	50±2%	Xylene	34 to 63ps	15		Lacquers for PVC leather cloth, walls, floor, metals, wood and cement coatings.
Replakryl 914	50±2%	Xylene	27 to 46	5	Excellent colour, gloss retention, exterior durability with soap & detergent resistance. Compatible with CAB & NC	Enamels & Lacquers for Walls, Floors, Metal, Wood Cement Tiles, Plastic etc. & as a modifying resin to improve the drying time/durability of other coating systems. Fast drying industrial coating
Replakryl 915	45±2%	Xylene	46 to 80	5	For drying excellent gloss retention	Lacquers for PVC leather cloth, Paver block coatings, Metallising over laqure
Replakryl 916	40±2%	Xylene	46 to 63	5	High molecular resin with excellent colour, gloss retention, exterior durability with soap, detergent & alcohol resistance	Enamels & Lacquers for Walls, Floors, Metal, Wood Cement Tiles, Plastic etc. & as a modifying resin to improve the drying time / durability of other coating systems. Fast drying
Replakryl 917	45 ± 2 %	Ethyl Acetate	4-6 ps	10	NC /CAB Compatible, Very fast drying. Excellent wheathering properties. Excellent flexibilty , Good gloss retention , tough and flexible coatings	Pencil Coating Lacquers, wood coatings, plastic coatings

ACRYLIC RESINS (THERMOSETTING)

Product Nomenclature	Non-Volatiles 50°C/30min.	Solvent	Viscosity in Stokes at 25°C(G)	Acid Value (max.) (mgs. of KOH/gm)	Characteristics	Recommended Usages
Replakryl 921	60±2%	Xylene	34 to 63ps	10	Excellent gloss, solvent, oil & petrol resistance	Industrial Auto refinish , GI and OEM B/C & C/C
Replakryl 922	60±2%	Xylene / CA	10-17 ps	10	Excellent gloss , solvent & Chemicals resistant Low baking	Automotive OEM (2/4 Wheelers) , G I Coatings & Domestic applications
Replakryl 923	60±2%	Xylene / Butanol	10 to 12	15	Excellent adhesion, gloss, colour retention	General purpose stoving. Finishes for OEM & domestic appliances
Replakryl 924	70±2%	Solvent CIX	30-70 ps	10	Low bake , excellent oil & Petrol resistance	Automotive OEM , G I Coatings, Domestic appliances can be used as 2K -PU
Replakryl 926	60±2%	Xylene / Butanol	10 to 17	15	Excellent adhesion to bare metal, excellent gloss, colour retention, solvent resistance	High quality Automotive OEM & domestic appliances

RESINS & PLASTICS LTD.

Regd. Off.: Plot No. A-8, Marol Industrial Estate of MIDC, Cross Road B, Street No.5, Andheri (E), Mumbai - 400 093. India. Tel.: +91- 22- 6198 7000 Email : info@resplast.com

Although the information contained in this Product Data Sheet is believed to be correct as of the date hereof, Resins & Plastics Ltd. makes no representation the completeness of accuracy in this Data Sheet. Those who use this product described herein must determine the appropriate manner for processing the product to ensure the safety and quality. In no event shall Resins & Plastics Ltd. be responsible for damages of any nature resulting from the use of or reliance upon the information contained herein.



ACRYLIC RESINS (FOR TWO PACK POLYURETHANE BASED SYSTEMS)

Product Nomenclature	% Non-Volatile 150°C/30min.	Solvent	Colour Gardner	Viscosity in Stokes at 25°C Gardener	Hydroxyl Value (max.) (mgs. of KOH/gm)	Characteristics	Recommended Usages
Replakryl 927	60±2	Xylene	1 Max.	22 - 34	45 - 50	Excellent gloss, fast drying / curing. Low isocyanate demand	High performance polyurethane based coatings with low polyisocyanate requirement
Replakryl 928	55±2	Xylene	1 Max.	17 - 27	50 - 55	Good gloss and cost effective due to low isocyanate demand. Excellent surface drying Excellent curing performance & good flexibility	High performance coatings with excellent flexibility and low isocyanate requirement
Replakryl 929	60±2	Xylene / MPA Cellosolve Acetate	1 Max.	27-34	90-95	Extremely fast cure & superb stain & chemical resistance, exceptional weatherability & excellent adhesion	Suitable for acid resistant paints, durable metal coatings, in aircraft finishes, fiber glass components/boats, plastics, etc.
Replakryl 930	60±2	Xylene	1 Max.	27-46	65-70	Air drying and Force drying	Coatings for Brass, Plastic, Aluminium, Plasticizer for acrylic polyols
Replakryl 932	60±2	Xylene / Butyl Acetate	1 Max.	12-17	140-150	Excellent gloss flow and durability	Vehicle refinishing in view of excellent durable and resistance properties primer / surface and top coat application
Replakryl 933	60±2	Xylene / Cellosolve Acetate/ Solvent EEP/ MEK	1 Max.	27-34	93-103	-do-	Industrial OEM (applicable to metal and plastic substrate), wood finish segment
Replakryl 938	60±2	Xylene	1 Max.	27-34	93-103	Air drying and Force drying	Vehicle refinishing in view of excellent durable and resistance properties primer / surface and top coat application
Replakryl 939	60±2	Xylene / Cellosolve Acetate	1 Max.	27-46	68-78	Excellent flow, gloss retention, weatherability, Excellent Flexibility / Impact Resistance	Suitable for coatings on plastics, wood, concrete finishes
Replakryl 940	70±2	Xylene / Cellosolve Acetate	1 Max.	22-34	60-80	Air drying and Force drying compatible with all type of replakryl resins	Interior Coatings on Metal furniture, Agriculture Machinery, Domestic Appliances
Replakryl 941	70±2	Xylene	1 Max.	98-148	65-75	Air drying and Force drying compatible with all type of replakryl resins	Interior Coatings on Metal furniture, Agriculture Machinery, Domestic Appliances
Replakryl 945	70±2	Xylene	1max	150-200 ps	60-80	Good gloss, DOI & Chemical resistance	Metal furniture, Agricultural machineries & Domestic appliances
Replakryl 946	60±2	Xylene / Bu- Acetate	0-1	17-35	85-95	Offer fast drying, with good flow and leveling property	Industrial, Auto refinish, glass and Wood Coating
Replakryl 947	75±2	Xylene	0-1	34-63	60-70	For single high DFT, excellent gloss and adhesion	Industrial coating and Auto refinish

RESINS & PLASTICS LTD.

Regd. Off.: Plot No. A-8, Marol Industrial Estate of MIDC, Cross Road B, Street No.5, Andheri (E), Mumbai - 400 093. India. Tel.: +91- 22- 6198 7000 Email : info@resplast.com

Although the information contained in this Product Data Sheet is believed to be correct as of the date hereof, Resins & Plastics Ltd. makes no representation the completeness of accuracy in this Data Sheet. Those who use this product described herein must determine the appropriate manner for processing the product to ensure the safety and quality. In no event shall Resins & Plastics Ltd. be responsible for damages of any nature resulting from the use of or reliance upon the information contained herein.



ACRYLIC RESINS (FOR TWO PACK POLYURETHANE BASED SYSTEMS)

Product Nomenclature	% Non-Volatile 150°C/30min.	Solvent	Colour Gardner	Viscosity in Stokes at 25°C Gardener	Hydroxyl Value (max.) (mgs. of KOH/gm)	Characteristics	Recommended Usages
Replakryl 950	70±2	Xylene / BU Acetate	0-1	46-98	90-105	Fast cure, chemical resistant, excellent flow and gloss properties	Industrial OEM, applicable to metal, wood and glass substrate
Replakryl 951	60 ± 2	Xylene/ BA	1max	36-63 ps	90-110	Good adhesion on Bare metals GI. Al, Cu, Brass, MS etc	Monocoat application, Auto refinshes
Replakryl 952	55±2	Xylene / Butyl Acetate	0-1	7-17	60-70	Excellent adhesion on Aluminium, Copper, Brass and MS.	Industrial Coating, bus body, small decorative metal articles
Replakryl 953	60±2%	Xylene	2	22-34 ps	90-110	Good metallic orientation, good gloss, impact resistance, compactible with CAB	Metalic base coat and clera coat for OEM /GI
Replakryl 954	70 ± 2	Xylene/ BA	1max	36-63 ps	120-140	Excellent gloss , solvent & Chemicals resistant	High quality refinishing coatings with excellent flow & gloss retention
Replakryl 955	70 ± 2	Butyl Acetate	1max	34-63 ps	120-140	High gloss & DOI , Good wherthering properties	High quality Auto refinshes
Replakryl 957	45 ± 2	Xylene/ MPA	1max	22-34 ps	20-40	Excellent adhesion on plastics coatings, Solvent & chemical resistant	Automotive C/C on metal & Plastics
Replakryl 959	70±2	Xylene	1max	80-100 ps	60-80	Good adhesion , High gloss & Chemical resistance	Top / Base coat in Automotive & GI coatings
Replakryl 961	70±2%	Xylene	2	98-146 ps	60-80	Excellent gloss, flow , flexibilty and Impact resistance	Industrial Auto refinsh, glass, OEM B/C & C/C
Replakryl 962	60±2%	Xylene	0-1	22-34 ps	70-80	Good gloss , DOI & Chemical resistance.	Industrial Auto refinsh, glass, OEM B/C & C/C
Replakryl 963	60±2	Xylene / Bu- Acetate	0-1	35-45	85-95	Offer fast drying, with good flow and leveling property	Industrial, Auto refinsh, glass and Wood Coating

REF - % OH CONTENT = OH VALUE / 33.3

RESINS & PLASTICS LTD.

Regd. Off.: Plot No. A-8, Marol Industrial Estate of MIDC, Cross Road B, Street No.5, Andheri (E), Mumbai - 400 093. India. Tel.: +91- 22- 6198 7000 Email : info@resplast.com

Although the information contained in this Product Data Sheet is believed to be correct as of the date hereof; Resins & Plastics Ltd. makes no representation the completeness of accuracy in this Data Sheet. Those who use this product described herein must determine the appropriate manner for processing the product to ensure the safety and quality. In no event shall Resins & Plastics Ltd. be responsible for damages of any nature resulting from the use of or reliance upon the information contained herein.