

### EPOXY DILUENTS

Product Nomenclature	Type	Colour (Gardner)	Viscosity at 25°C	Epoxide equivalent	Specific Gravity at 30°C	Recommended Usages
Replacure 193	Aliphatic epoxy diluent	2 Max.	2 cps max.	148 – 165	0.93 ± 0.01	Tooling, electrical applications, flooring.
Replacure 198	Aliphatic epoxy diluent	1 Max.	5 – 10 cps.	280 – 310	0.9. ± 0.01	Flooring, casting, tooling, laminating, potting, etc.

### POLYURETHANE RESINS

Product Nomenclature	Type	Colour (Gardner/ Appearance)	Viscosity at 25°C on Gardner (in Stokes)	Isocyanate Content (%)	% Non-volatiles at 120°C/1hr.	Recommended Usages
Replacure 150	Aromatic isocyanate adduct in ethyl acetate	2 Max.	0.062 – 0.14	9 ± 0.5	51 ± 1	Laminating adhesive, chemical and abrasion resistant coatings.
Replacure 152	Aromatic isocyanate adduct in ethyl acetate	3 Max.	10 – 22	13 ± 0.5	74 ± 1	Laminating adhesive, sealants, chemicals and abrasion resistant coatings, coatings for sports goods.
Replacure 155	Phenol blocked isocyanate	Pale yellow to pinkish lumps	95 – 100°C (B & R softening point)	12 ± 0.5	N A	Wire enamels, insulating varnishes, laminating adhesives, chemical & abrasion resistant coatings.
Replacure 174	Aromatic isocyanate adduct in cellosolve acetate : ethyl acetate : : 3 : 1	3 Max.	0.65 – 3.0	10.5 – 11%	60 ± 2	Sealants and chemical resistant coatings.

### OIL MONOGLYCERIDES

Product Nomenclature	Type	Appearance	S D S Tolerance	Recommended Usages
Replacure 131	Linseed oil monoglyceride	Yellowish Brown	1 : 5 Min.	As pigment dispersion agent for darker shades of paints
Replacure 132	Coconut oil monoglyceride	Pale Yellow	1 : 10 Min.	As pigment dispersion agent for lighter shades of paints